



Argo-braze™ 562 – Silver Brazing Filler Metal

Argo-braze™ 562 is a specialised, cadmium free, zinc free silver brazing filler metal. Thus it has been used for furnace brazing operations where the evolution of zinc fume would not be acceptable. Its principle use is for the fluxless brazing of stainless steel in dry, high hydrogen content reducing atmospheres. Joints brazed with Argo-braze™ 562 exhibit good elevated temperature properties up to 425°C.

Argo-braze™ 562 has a long and high melting range and produces large fillets. It is consequently prone to liquefy (separate into low and high melting constituents) if it is heated slowly through its melting range. For this reason rapid heating methods should be employed wherever possible.

Composition:	56% Ag, 42%Cu, 2%Ni
Conforms to:	AWS A5.8 Bag-13a, AMS 4765, ISO 17672:2010 Ag 456
Melting range:	770-895°C

Uses for This Product

Argo-braze™ 562 is used for flux less reducing atmosphere brazing or vacuum brazing of ferrous and non-ferrous metals, particularly stainless steel joints that will be expected to work under elevated temperature service conditions such as aerospace components.

Conditions for Use

This product can be used for flux-less brazing in a hydrogen based reducing atmosphere or in vacuum. Flux may be required to promote satisfactory filler metal wetting in hydrogen based reducing atmospheres that are not sufficiently dry. When vacuum brazing a partial pressure brazing technique should be used to suppress vapourisation of the silver within the alloy.

If used for brazing in air it should be used in conjunction with a high temperature flux such as Tenacity™ No. 5 Flux or Tenacity™ No. 125 Flux. A rapid heating method such as induction heating is recommended to avoid the problems of liquation.

Product Availability

Manufactured to order only.

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.

This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey® name and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



Johnson Matthey

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: mj@matthey.com

[www: jm-metaljoining.com](http://www.jm-metaljoining.com)