



Argo-braze™ 72NiV – Silver Brazing Filler Metal

Argo-braze™ 72NiV is a modified version of the silver-copper brazing filler metal Argo-braze™ 72V. It has a nominal 0.5% addition of nickel that improves the filler metal's wetting characteristics on ferrous and nickel based parent metals and somewhat reduces the alloy's flow properties making it more sluggish.

Like Argo-braze™ 72V this filler metal can be manufactured to meet vacuum tube grade requirements with low and controlled levels of volatile impurities. Consequently it can be used on vacuum tube devices that operate at moderate temperatures, and where the presence of volatile elements might otherwise be detrimental to the performance of the component

Where ceramics are being brazed to a low expansion nickel alloy care should be taken (nickel plating / stress relieving) to prevent intergranular penetration (liquid metal stress cracking) of the nickel alloy.

Composition: 71.5%Ag, 28%Cu, 0.5%Ni
Conforms to: AWS A5-8 BVAg-8b
Melting range: 780-795°C

Uses for This Product

Argo-braze™ 72NiV is used for brazing silver, copper, nickel and ferrous-based parent metals as well as metalised ceramics. Typical applications include components for vacuum tube devices.

Conditions for Use

This product can be used to braze in hydrogen, an inert atmosphere or in a vacuum without the need for a flux. When vacuum brazing a partial pressure brazing technique should be used to prevent the vaporisation of the silver within the alloy.

Product Availability

Special order only.

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.

This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey® name and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



Johnson Matthey

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: mj@matthey.com

[www: jm-metaljoining.com](http://www.jm-metaljoining.com)