



Argo-braze™ 72V – Silver Brazing Filler Metal

Argo-braze™ 72V is a silver-copper brazing filler metal with a eutectic composition, and has a melting point of 778°C unlike most other brazing filler metals that have a melting range.

It is manufactured to meet vacuum tube grade requirements with low and controlled levels of volatile impurities. Consequently it can be used on vacuum tube devices that operate at moderate temperatures and where volatile elements might be detrimental to the performance of the component.

Having a single melting temperature of 778°C makes the alloy very free flowing and able to penetrate narrow joint gaps. On silver and copper parent materials the flow of the alloy is reduced and the re-melt temperature is increased due to the filler metal taking silver or copper into solution when molten. Exercising careful control of the brazing cycle brazing temperatures and time at temperature can reduce this effect.

Argo-braze™ 72V shows only limited wetting on iron and nickel base metals and on cemented tungsten carbides.

Where ceramics are being brazed to a low expansion nickel alloy, care should be taken (nickel plating / stress relieving) to prevent intergranular penetration (liquid metal stress cracking) of the nickel alloy.

Argo-braze™ 72V is standardly supplied as EN 1044 vacuum grade V1, but it can also be supplied in the vacuum grade V2, both of which are suitable for vacuum tube applications. The alloy can also be supplied as the non-vacuum tube grade material EN 1044 AG401.

Argo-braze™ 72V was formerly known as Silver-Copper Eutectic™.

Composition:	72%Ag, 28%Cu
Conforms to:	EN1044 AG401, V1 or V2 grades, AWS A5-8 BAg-8, ISO 17672:2010 Ag 272 V1
Melting point:	778°C

Uses for This Product

Argo-braze™ 72V is used for brazing silver, copper and nickel based alloys as well as metalised ceramics. Typical applications include components for vacuum tube devices.

Conditions for Use

This product can be used to braze in hydrogen, an inert atmosphere or in a vacuum without the need for a flux. When vacuum brazing a partial pressure brazing technique should be used to prevent the vaporisation of the silver within the alloy.

Product Availability

Special order only.

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.
This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey® name and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



Johnson Matthey

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: mj@matthey.com

www.jm-metaljoining.com