



Sil-fos™ 6 – Silver Copper Phosphorus Brazing Filler Metal

Sil-fos™ 6 is a 6% silver-copper-phosphorus brazing filler metal, which is used to braze copper and copper alloys. When brazing copper the phosphorus within the alloy imparts a metallurgical based self-fluxing capability. When Sil-fos™ 6 is used to join copper alloys (such as brass, bronze or gun metal) a separate flux will be required because the self-fluxing action only occurs on copper (see below for details).

This filler metal should not be used to braze iron containing materials like carbon or stainless steels or nickel containing materials as the phosphorus within the filler metal will form brittle, intermetallic, phosphide compounds at the joint interface. Sil-fos™ 6 is not suitable for use in sulphurous atmospheres at elevated service temperatures.

When selecting a brazing filler metal from the Sil-fos™ range it is necessary to understand about the flow and ductility of the different products. Phosphorus is the key element, the higher this is the more free flowing the filler metal, but the lower its ductility. Silver is used to improve the filler metal's ductility, but reduces its flow properties.

Sil-fos™ 6 is one of the most free flowing filler metals from the Sil-fos™ range. However, due to its high phosphorus content it is one of the least ductile. The low ductility of the alloy imparts it with glass like properties, making it both 'notch' sensitive and sensitive to impact type loadings. This filler metal should therefore not be used in applications involving exposure to strong vibration, impact loads or where some deformation of the joint might be expected in service. In such circumstances the use of Sil-fos™ 5 or Sil-fos™ should be considered. Sil-fos™ 6 is best suited for making copper joints that are of the true capillary type and where tight joint clearances of 0.025-0.075 mm are used. When used in such joints, the poor mechanical properties of the filler metal are exposed and satisfactory joints, suitable for use in all but the most extreme conditions can generally be produced.

Composition:	6%Ag, 86.75%Cu, 7.25%P
Conforms to:	AWS A5.8 BCuP-4, ISO 17672:2010 CuP 283
Melting range:	644-718°C

Uses for This Product

Sil-fos™ 6 is extensively used in refrigeration and air conditioning applications for flux-free brazing of copper pipes and tubes. It is also used for joining copper in electrical engineering applications.

Conditions for Use

Flame heating methods are most often used for brazing with Sil-fos™ 6. When used as a pre-form rapid heating to the brazing temperature is required to avoid liquation (separation of low and high melting phases in the alloy).

For brazing copper to copper no flux is needed, as Sil-fos™ 6 is self-fluxing in this case.

For use on copper alloys a separate flux is required and Easy-flo™ Flux is suitable. For prolonged heating cycles on larger components Tenacity™ No.4A Flux or Tenacity™ No.5 Flux may be required.

Product Availability

Brazing Rods	1.5mm, 2mm, 2.5mm, 3mm
Wire	1mm to 3mm
Other	Braze-pastes, on request

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.
This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey name® and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



Johnson Matthey

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: mj@matthey.com

www.jm-metaljoining.com