www: im-metalioining.com



## Silver-flo™ 33 – Cadmium Free Silver Brazing Filler Metal

Silver-flo<sup>™</sup> 33 is a cadmium free silver brazing filler metal. It shows free flowing characteristics melting over a short, but comparatively high, temperature range (700-740°C). It is a good brazing filler metal that has been used as the second filler metal in a three step sequential brazing process along with Silver-flo<sup>™</sup> 16 and Silver-flo<sup>™</sup> 55. Silver-flo<sup>™</sup> 33 is not widely used today. Optimum joint gaps at brazing temperature are 0.075-0.2mm.

**Composition:** 33%Ag, 33.5%Cu, 33.5%Zn **Conforms to:** Proprietary JM specification

Melting range: 700-740°C

## **Uses for this Product**

This filler metal can be used to join all the common engineering materials (excluding aluminium) – such as copper, copper alloys (including, brasses, bronzes, gun metal, nickel silvers, aluminium bronze, copper nickel) and steel (including, mild, carbon, tool steel, stainless steels and low alloy steel). It may be used for brazing tungsten carbide and PCD segments however where cracking of the carbide or wetting of the filler metal may be an issue specialised silver brazing filler metals containing nickel / manganese are often preferred.

## **Conditions for Use**

This filler metal is mainly used for brazing in air with a flux. In most cases Easy-flo™ flux can be used in conjunction with Silver-flo™ 33. However, flux selection is application dependent. Please refer to JM technical department or flux product datasheets before selecting a flux.

## **Product Availability**

Rod 1.5mm
Flux Coated Rod On request
Wire On request
Strip On request
Foil On request
Braze-pastes On request

Telephone: +44 (0) 1763 253200

Other Rings, Preformed Shapes

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc sscumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.

This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo©, Johnson Matthey name© and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.