



## Silver-flo™ 40 – Cadmium Free Silver Brazing Filler Metal

Silver-flo™ 40 is a very widely used cadmium free silver brazing filler metal. It offers a combination of medium melting temperature and flow characteristics. It can be used to fill gaps that cannot be tightly controlled. These properties make it a popular choice as an alternative to the higher silver content Silver-flo™ filler metals (Silver-flo™ 55 and 56). Silver-flo™ 40 is widely used as a general purpose silver brazing filler metal as well as in joining copper to steel in refrigeration pipe work.

It should be noted that this filler metal contains tin and may be described as being 'hot-short'. It should not be quenched from high temperatures (in excess of 300°C) and care should be taken when it is used to braze components with widely differing coefficients of thermal expansion as in both cases cracking of the joints may occur.

Optimum joint gaps at brazing temperature are 0.075-0.2mm.

<b>Composition:</b>	40%Ag, 30%Cu, 28%Zn, 2%Sn
<b>Conforms to:</b>	ISO 17672:2010 Ag 140, AWS A5.8 BAg-28, formerly EN1044 1999 AG105
<b>Melting range:</b>	660-710°C

### Uses for This Product

Silver-flo™ 40 can be used to join most common engineering metals - copper, copper alloys including, brasses, bronzes, gun metal, nickel silver, aluminium bronze, copper nickel, steels including, mild, carbon, tool steel, stainless steels, low alloy steel. This alloy is not normally recommended for brazing tungsten carbide and PCD segments where lower melting or nickel / manganese containing silver brazing filler metals are often preferred.

### Conditions for Use

This filler metal is mainly used for brazing in air with a flux. In most cases Easy-flo™ Flux can be used in conjunction with Silver-flo™ 40. However, flux selection is application dependent. Please refer to Johnson Matthey technical department or flux product datasheets before selecting a flux.

### Product Availability

Rod	1.5mm, 2mm, 2.5mm, 3mm
Flux Coated Rod	1.5mm, 2mm
Wire	0.75mm, 0.8mm
Strip	3 x 1mm, 1.5 x 1mm, 3 x 1.5mm
Foil	20 x 0.15mm
Braze-pastes	On request
Others	Rings, Preformed Shapes

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.

This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey name® and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



**Johnson Matthey**

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: [mj@matthey.com](mailto:mj@matthey.com)

[www.jm-metaljoining.com](http://www.jm-metaljoining.com)